Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

Lab ID	:	**CP-2018-03-07-08** **Date: 12-03-2018**
Customer	:	Assistant Executive Engineer, Yelahanka Sub division, BBMP, Bangalore.
Address	:	Yelahanka Sub division, BBMP, Bangalore.
Project Name	:	Improvements to roads and drains at balance portion in kamakshamma layout and surrounding areas in ward No.02 of Yelahanka Sub Division.
Agency	:	Sri.Y.A Dhanashekar, No.10, K.H.B Colony Yelahanka, Bangalore-64
Customer's Reference	:	EE(YNK.D)E-PMT-14/W.O/000122/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-03-2018
Sample ID No	:	2018-03-07-08 /06
Sample Type /Size	:	100mm thick Precast Cover Slab
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete
Date of test	:	08/03/2018

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	75.51	100.48	1.216	4477	91.2	20.4	18.9	23.7
2	Cover Slab-2	75.49	100.52	1.222	4475	95.3	21.3	19.8	24.8
3	Cover Slab-3	75.50	100.51	1.218	4476	91.9	20.5	19.1	23.9

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE-2
A.E.E

FOR CIVIL Pro.

CIVIL PRO BANGALORE Sig..... Date.....

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

AE-2

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE KERB STONE

Lab ID : CP-2018-03-07-08 **Date: 12-03-2018**

Customer : Assistant Executive Engineer, Yelahanka Sub division, BBMP, Bangalore.

Address : Yelahanka Sub division, BBMP, Bangalore.

Project Name : Improvements to roads and drains at balance portion in kamakshamma layout and surrounding areas in ward No.02 of Yelahanka Sub Division.

Agency : Sri.Y.A Dhanashekar, No.10, K.H.B Colony Yelahanka, Bangalore-64

Customer's Reference : EE(YNK.D)E-PMT-14/W.O/000122/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 07-03-2018

Sample ID No : 2018-03-07-08 /04

Sample Type /Size : CC Kerb Stone/ 450*165*400mm

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete

Date of test : 08/03/2018

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	Kg	(Sq.mm)	(KN)	(N/mm2)	(N/mm2)	(N/mm2)
1	A	100.01	165.51	2.864	7854	142.1	18.1	16.8	21.0
2	B	100.03	165.49	8.793	7857	145.2	18.5	18.5	23.1
3	C	100.01	165.50	8.815	7854	145.1	18.5	18.5	23.1

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE-2 A.E.E

AE-2

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

Lab ID	:	**CP-2018-03-07-08** **Date: 12-03-2018**
Customer	:	Assistant Executive Engineer, Yelahanka Sub division, BBMP, Bangalore.
Address	:	Yelahanka Sub division, BBMP, Bangalore.
Project Name	:	Improvements to roads and drains at balance portion in kamakshamma layout and surrounding areas in ward No.02 of Yelahanka Sub Division.
Agency	:	Sri.Y.A Dhanashekar, No.10, K.H.B Colony Yelahanka, Bangalore-64
Customer's Reference	:	EE(YNK.D)E-PMT-14/W.O/000122/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-03-2018
Sample ID No	:	2018-03-07-08 /05
Sample Type /Size	:	200mm thick Precast Cover Slab
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete
Date of test	:	08/03/2018

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	150.04	200.11	2.890	17678	275.9	15.6	14.5	18.1
2	Cover Slab-2	150.05	200.09	2.885	17680	278.1	15.7	14.6	18.3
3	Cover Slab-3	150.07	200.21	2.854	17685	277.5	15.7	14.6	18.2

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE-2 A.E.E

AE 02

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2018-03-22-08

Date: 26/03/2018

Customer : Assistant Executive Engineer, Yelahanka Sub division, BBMP, Bangalore.

Address : Yelahanka Sub division, BBMP, Bangalore.

Project Name : Improvements to roads and drains at balance portion in kamakshamma layout and surrounding areas in ward No.02 of Yelahanka Sub Division.

Agency : Sri.Y.A Dhanashekar, No.10, K.H.B Colony Yelahanka, Bangalore-64

Customer's Reference : EE(YNK.D)E-PMT-14/W.O/000122/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 22-03-2018

Sample ID No : 2018-03-22-08 /01

Customer ID : Drain concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 26/03/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain concrete	M20	19/03/2018	26/03/2018	150.31 X 150.64 X 150.77	22643	8.098	412.1	18.2	17.6
2	Drain concrete	M20	19/03/2018	26/03/2018	150.49 X 151.68 X 150.97	22826	8.158	390.3	17.1	
3	Drain concrete	M20	19/03/2018	26/03/2018	150.33 X 150.45 X 151.26	22617	8.174	398.1	17.6	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE-2 A.E.E

AE-2

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 16/04/2018

Lab ID	:	CP-2018-03-22-08
Customer	:	Assistant Executive Engineer, Yelahanka Sub division, BBMP, Bangalore.
Address	:	Yelahanka Sub division, BBMP, Bangalore.
Project Name	:	Improvements to roads and drains at balance portion in kamakshamma layout and surrounding areas in ward No.02 of Yelahanka Sub Division.
Agency	:	Sri.Y.A Dhanashekar, No.10, K.H.B Colony Yelahanka, Bangalore-64
Customer's Reference	:	EE(YNK.D)E-PMT-14/W.O/000122/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	22-03-2018
Sample ID No	:	2018-03-22-08 /02
Customer ID	:	Drain concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	16/04/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain concrete	M20	19/03/2018	16/04/2018	151.42 X 150.35 X 150.28	22766	8.175	525.9	23.1	23.2
2	Drain concrete	M20	19/03/2018	16/04/2018	151.44 X 150.39 X 150.25	22775	8.198	539.8	23.7	
3	Drain concrete	M20	19/03/2018	16/04/2018	150.47 X 150.66 X 150.69	22670	8.135	516.9	22.8	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE-2 / M.E.E

AE-2

FOR CIVIL Pro.

CIVIL Pro BANGALORE Sig Date

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2018-03-22-08

Date: 26/03/2018

Customer : Assistant Executive Engineer, Yelahanka Sub division, BBMP, Bangalore.

Address : Yelahanka Sub division, BBMP, Bangalore.

Project Name : Improvements to roads and drains at balance portion in kamakshamma layout and surrounding areas in ward No.02 of Yelahanka Sub Division.

Agency : Sri.Y.A Dhanashekar, No.10, K.H.B Colony Yelahanka, Bangalore-64

Customer's Reference : EE(YNK.D)E-PMT-14/W.O/000122/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 22-03-2018

Sample ID No : 2018-03-22-08 /03

Customer ID : Drain Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 26/03/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Concrete	M20	19/03/2018	26/03/2018	149.65 X 151.22 X 149.78	22630	8.152	393.8	17.4	17.0
2	Drain Concrete	M20	19/03/2018	26/03/2018	151.33 X 149.80 X 151.44	22669	8.197	387.6	17.1	
3	Drain Concrete	M20	19/03/2018	26/03/2018	151.85 X 150.47 X 150.99	22849	8.161	377.0	16.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE-2 A.E.E

AE-12

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2018-03-22-08 **Date: 16/04/2018**

Customer : Assistant Executive Engineer, Yelahanka Sub division, BBMP, Bangalore.

Address : Yelahanka Sub division, BBMP, Bangalore.

Project Name : Improvements to roads and drains at balance portion in kamakshamma layout and surrounding areas in ward No.02 of Yelahanka Sub Division.

Agency : Sri.Y.A Dhanashekar, No.10, K.H.B Colony Yelahanka, Bangalore-64

Customer's Reference : EE(YNK.D)E-PMT-14/W.O/000122/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 22-03-2018

Sample ID No : 2018-03-22-08 /04

Customer ID : Drain concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 16/04/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain concrete	M20	19/03/2018	16/04/2018	150.41 X 150.99 X 150.32	22710	8.168	547.3	24.1	23.7
2	Drain concrete	M20	19/03/2018	16/04/2018	150.77 X 150.98 X 150.33	22763	8.195	528.1	23.2	
3	Drain concrete	M20	19/03/2018	16/04/2018	150.97 X 150.33 X 150.97	22695	8.147	537.9	23.7	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE-2 A.E.E

AE-II

Page 1/1

****End of Report****

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2018-03-07-08** **Date: 10-03-2018**
Customer	:	Assistant Executive Engineer, Yelahanka Sub division, BBMP,
Address	:	Yelahanka Sub division, BBMP, Bangalore.
Project Name	:	Improvements to roads and drains at balance portion in kamakshamma layout and surrounding areas in ward No.02 of Yelahanka Sub Division.
Agency	:	Sri.Y.A Dhanashekar, No.10, K.H.B Colony Yelahanka, Bangalore-64
Customer's Reference	:	EE(YNK.D)E-PMT-14/W.O/000122/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-03-2018
Sample ID No	:	2018-03-07-08 /01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	08-03-2018
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	2.28	–
2	Finess by Air permeablity method (m^2/kg,Min)	274.6	225m^2/kg, Min
3	Density (gm/cc)	3.12	–
4	Standard Consistency (%)	29%	Not specified
5	Initial Setting time	155 minutes	Not less than 30 minutes
6	Final Setting time	240 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE-2
A.E.E
AE-2

FOR CIVIL Pro.

CIVIL Pro Sig Date BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	CP-2018-03-07-08
Customer	:	Assistant Executive Engineer, Yelahanka Sub division, BBMP, Bangalore. **Date: 05-04-2018**
Address	:	Yelahanka Sub division, BBMP, Bangalore.
Project Name	:	Improvements to roads and drains at balance portion in kamakshamma layout and surrounding areas in ward No.02 of Yelahanka Sub Division.
Agency	:	Sri.Y.A Dhanashekar, No.10, K.H.B Colony Yelahanka, Bangalore-64
Customer's Reference	:	EE(YNK.D)E-PMT-14/W.O/000122/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-03-2018
Sample ID No	:	2018-03-07-08 /01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	08-03-2018
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	29.0N/mm^2	Not less than 27 N/mm^2
2	7 Days	38.0N/mm^2	Not less than 37 N/mm^2
3	28 Days	55.0N/mm^2	Not less than 53 N/mm^2

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

A.E.E
AE-02

FOR CIVIL Pro.
CIVIL Pro Sig..... Date..... BANGALORE
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2018-03-07-08** **Date: 10-03-2018**
Customer	:	Assistant Executive Engineer, Yelahanka Sub division, BBMP, Bangalore.
Address	:	Yelahanka Sub division, BBMP, Bangalore.
Project Name	:	Improvements to roads and drains at balance portion in kamakshamma layout and surrounding areas in ward No.02 of Yelahanka Sub Division.
Agency	:	Sri.Y.A Dhanashekar, No.10, K.H.B Colony Yelahanka, Bangalore-64
Customer's Reference	:	EE(YNK.D)E-PMT-14/W.O/000122/2017-18
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	07-03-2018
Sample ID No	:	2018-03-07-08 /02(a)
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	07-03-2018

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	342	342	2.3	97.7	90-100
3	20 mm	5439	5781	38.5	61.5	30-70
4	10 mm	4579	10360	69.1	30.9	10-35
5	4.75 mm	4260	14620	97.5	2.5	0-5
6	Pan	380	15000	100.0	0	---

AE-2 A.E.E

AE-2

CIVIL PRO Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2018-03-07-08** **Date: 10-03-2018**

Sample ID No : 2018-03-07-08 /02(a)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	12.4	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.6	
3	Specific Gravity	2.67	–
4	Bulk Density(Loose) (Kg/l)	1.54	–
5	Bulk Density(Compacted) (Kg/l)	1.58	–
6	Water Absorption(%)	0.21	–

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE-2
A.E.E
ACCO

FOR CIVIL Pro.

CIVIL PRO BANGALORE Sig Date

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	CP-2018-03-07-08 **Date: 09-03-2018**
Customer	:	Assistant Executive Engineer, Yelahanka Sub division, BBMP, Bangalore.
Address	:	Yelahanka Sub division, BBMP, Bangalore.
Project Name	:	Improvements to roads and drains at balance portion in kamakshamma layout and surrounding areas in ward No.02 of Yelahanka Sub Division.
Agency	:	Sri.Y.A Dhanashekar, No.10, K.H.B Colony Yelahanka, Bangalore-64
Customer Reference	:	EE(YNK.D)E-PMT-14/W.O/000122/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-03-2018
Sample ID No	:	2018-03-07-08 /02(b)
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	07-03-2018

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	214	214	4.3	95.7	90-100
3	10 mm	2435	2649	53.0	47.0	25-55
4	4.75 mm	2134	4783	95.7	4.3	0-10
5	Pan	217	5000	100	0	–

AE-2
A.E.E

AE-2

CIVIL PRO
Sig.....
Date.....
BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2018-03-07-08** **Date: 09-03-2018**

Sample ID No : 2018-03-07-08 /02(b)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	13.2	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	12.4	
3	Specific Gravity	2.69	–
4	Bulk Density(Loose) (Kg/l)	1.48	–
5	Bulk Density(Compacted) (Kg/l)	1.53	–
6	Water Absorption(%)	0.22	–
7	Aggregate crushing Value(%)	22.9	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	22.1	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE-2 A.E.E

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signature
Quality Manager

End of Report

AE-2

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Date: 09-03-2018

Lab ID	:	**CP-2018-03-07-08**
Customer	:	Assistant Executive Engineer, Yelahanka Sub division, BBMP, Bangalore.
Address	:	Yelahanka Sub division, BBMP, Bangalore.
Project Name	:	Improvements to roads and drains at balance portion in kamakshamma layout and surrounding areas in ward No.02 of Yelahanka Sub Division.
Agency	:	Sri.Y.A Dhanashekar, No.10, K.H.B Colony Yelahanka, Bangalore-64
Customer's Reference	:	EE(YNK.D)E-PMT-14/W.O/000122/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-03-2018
Sample ID No	:	2018-03-07-08 /03
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	07-03-2018
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	82	82	8.2	91.8	90-100	90-100	90-100	95-100
3	2.36 mm	133	215	21.5	78.5	60-95	75-100	85-100	95-100
4	1.18 mm	179	394	39.4	60.6	30-70	55-90	75-100	90-100
5	600 micron	186	580	58.0	42.0	15-34	35-59	60-79	80-100
6	300 micron	173	753	75.3	24.7	5-20	8-30	12-40	15-50
7	150 micron	156	909	90.9	9.1	0-10	0-10	0-10	0-15
8	Pan	91	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

AE-2 A.E.E

AE-2

CIVIL PRO Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST RESULTS OF STEEL

Lab ID	:	**CP-2018-03-07-08**
Customer	:	Assistant Executive Engineer, Yelahanka Sub division, BBMP, Bangalore.
Address	:	Yelahanka Sub division, BBMP, Bangalore.
Project Name	:	Improvements to roads and drains at balance portion in kamakshamma layout and surrounding areas in ward No.02 of Yelahanka Sub Division.
Agency	:	Sri.Y.A Dhanashekar, No.10, K.H.B Colony Yelahanka, Bangalore-64
Customer's Reference	:	EE(YNK.D)E-PMT-14/W.O/000122/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-03-2018
Sample ID No	:	2018-03-07-08 /04
Sample Type	:	Sunvik
Reference to BIS codes	:	IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2012.
Date of test:	:	08-03-2018

Date: 09-03-2018

Sl.No	Identification of sample	Grade of the sample	Diameter of the steel bar	Weight of the sample	Yield stress	Tensile strength	Elongation	Bend test	Rebend test
			(mm)	(kg/m)	(N/mm2)	(N/mm2)	(%)		
1	Sunvik	Fe500	8	0.392	542	672	20.0%	Satisfactory	Satisfactory
2	Sunvik	Fe500	10	0.613	564	682	20.0%	Satisfactory	Satisfactory
3	Sunvik	Fe500	12	0.878	585	695	19.0%	Satisfactory	Satisfactory

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE-2
A.E.E

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

AE-2

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES |